- Ready-to-use
- Resistant to light foot traffic
- Up to 24 months shelf life in its original packaging
- For exposed continuous waterproofing layers
- Quick, easy installation
- Waterproof
- Flexible with high crack-bridging properties
- Excellent bond on a multitude of surfaces
- High resistance to atmospheric agents
- Non-toxic and non-flammable



PRODUCTS FOR CERAMICS AND STONE MATERIALS

PRODUCTS FOR RESILIENT AND TEXTILE MATERIALS

PRODUCTS FOR WOODEN FLOORING

PRODUCTS FOR CEMENTITIOUS AND RESIN FLOORING

PRODUCTS FOR ACOUSTIC INSULATION

PRODUCTS FOR BUILDING

ADMIXTURES FOR CONCRETE

PRODUCTS FOR STRUCTURAL STRENGTHENING

PRODUCTS FOR THE REPAIR OF MASONRY

PRODUCTS FOR THERMAL INSULATION

WALL PROTECTIVE AND DECORATIVE COATINGS

PRODUCTS FOR WATERPROOFING

PRODUCTS FOR UNDERGROUND CONSTRUCTIONS

ELASTIC SEALANTS AND ADHESIVES

GRINDING AIDS FOR CEMENT

HEADQUARTERS
MAPEI SpA
Via Cafiero, 22 - 20158 Milan
Tel. +39 02 37673.1
Fax +39 02 37673.214
Internet: www.mapei.com
E-mail: mapei@mapei.it

Aquaflex Roof Can it be any easier than this? Ready-to-use flexible liquid membrane with fibres for continuous waterproofing layers on exposed external surfaces







Aquaflex Roof

Ready-to-use flexible liquid membrane with fibres for continuous waterproofing layers on exposed external surfaces

WHERE TO USE

Waterproof exposed surfaces for:

- flat roofs;
- balconies and terraces;
- guttering and downpipes;
- cupolas and curved roofs.

AQUAFLEX ROOF MAY BE APPLIED ON:

- ceramic and stone coatings;
- cementitious screeds and screeds made using special binders (Topcem and Topcem Pronto);
- concrete;
- asbestos cement;
- bitumen sheaths;
- wood.



An example of old terracotta floor requiring treatment before applying **Aquaflex Roof**



Waterproofing fraction joints with Mapeband fixed with Aquaflex Roof

Technical Data	
Product identity	
Consistency:	paste
Colours:	brick red, grey
Density (kg/m³):	1,32
Dry solids content (%):	62
Application data	
Application temperature range:	from +5°C to +35°C
Waiting time between first and second coat:	approx. 8-12 hours
Set to light foot traffic:	12 hours at +23°C
Final performance	
Elongation at breakage (DIN 53504) (%):	300
Tensile strength (DIN 53504) (N/mm²):	1.1
Packaging:	20 kg drums
Consumption:	1.3 kg/m² per mm of thickness



Cleaning a substrate before applying Aquaflex Roof



Application of Aquaflex Roof with a long-haired roller



