

Associated Products

Planiprep Skimcoat

COMPLETE YOUR PROJECT WITH...

Fine smoothing, finishing
and skim-coat mortar

Surface Primers

Eco Prim T

Eco Prim Grip



MK706130 06/14

Eco Adhesives



Try our Ultrabond ECO range of adhesives on your next project.

Damp Proof Membranes

Mapeproof ESM

Mapeproof One Coat

Mapeproof 1k Turbo



Planiprep Skimcoat

Technical Data

PRODUCT IDENTITY

Colour:	Grey
Consistency:	Paste
Packaging weight:	10kg

PRODUCT PROPERTIES

Mixing Ratio:	50 - 55%
Thixotropic properties:	Yes
pH of the mix:	12
Application Temp Range:	+5°C to +30°C
Pot Life:	25 minutes
Setting Time:	30 minutes at 3mm
Set to light foot traffic:	2 hours at 3mm
Waiting Time before subsequent bonding:	4 - 6 hours at 3mm
Storage:	12 months in a dry place
Cleaning/rinsing:	Planiprep Skimcoat can be rinsed from hands and tools with water if not yet set

Where to use

Planiprep Skimcoat is a fine polymer-modified cement-based skim coating and finishing mortar up to 3mm thick, used for the repairing, levelling and feathering of uneven sub floors, joints and screw-holes in plywood and other minor surface defects.

Floor coverings may be bonded directly to **Planiprep Skimcoat** once it has sufficiently cured after approximately 4 - 6 hours.

Advantages

- **Planiprep Skimcoat** can be used as a levelling compound as well as a skim-coat.
- For easy application **Planiprep Skimcoat** is best applied using a flat edged steel trowel after mixing with a low speed mixer to ensure a smooth lump-free consistency is achieved.
- **Planiprep Skimcoat** can be applied over joints and screw-holes to repair and level the surface.
- **Planiprep Skimcoat** can be used with our Damp Proof Membrane range at minimum of 3mm.
- **Planiprep Skimcoat** can also be used after applying a coat of **Eco Prim T** to consolidate and provide uniform absorbency on dusty or highly porous substrates.

For more technical information please visit our website www.mapei.co.uk and search for 'Planiprep Skimcoat' in the product search box.