

DECLARATION OF PERFORMANCE N. CPR-IT1/0839

- 1) Unique identification code of the product-type: **iSCREE 24**
- 2) Intended uses: **Deformed polyolefinic fibres (Class II, length 24 mm, diameter 0,90 mm) for structural use in concrete, mortar or grout**
- 3) Manufacturer: **MAPEI S.p.A. – Via Cafiero, 22 – 20158 Milan – Italy - www.mapei.it**
- 4) Systems of AVCP: **System 3**
- 5) Harmonized standards: **EN 14889-2:2006**

Notified bodies: **the notified laboratory Tecnoprove S.r.l., N. 0925, carried out the assessment of the performance on the basis of testing on samples taken by the manufacturer.**

- 6) Performances declared:

Essential characteristics	Performances
Tensile properties / Modulus of elasticity:	
- tensile strength:	280 N/mm²
- elastic modulus:	NPD
Effect on consistence of concrete:	
- increase of Vebè time with 1 kg/m ³ fibres:	1,2 s
Effect on strength of concrete:	NPD
Release of dangerous substances:	NPD

- 7) REACH information: this is an article in accordance with Article 3 of the REACH Regulation (EC) no. 1907/2006 and pursuant to Article 31 and 33 of the above-mentioned Regulation does not require any Safety Data Sheet. While using the product, pay attention to the recommendations written in the Technical Data Sheet and to the safety requirements laid down in the workplace.

The performance of the product identified above is in conformity with the set of declared performances.

This declaration of performance is issued, in accordance with Regulation (EU) no. 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by: **Lorenzo Martino – Corporate Quality Management**

Milan, 04/05/2020





DoP in Pdf format are available in the Mapei website.

Revision 0 notes:	First issue following incorporation into Mapei Spa
-------------------	--

iSCREE 24
CE MARKING
Annex to DoP N. CPR-IT1/0839



 0925	 Via Cafiero, 22 – 20158 Milano (Italy) www.mapei.it						
<p>20 CPR-IT1/0839 EN 14889-2 iSCREE 24</p> <p><i>Deformed polyolefinic fibres (Class II, length 24 mm, diameter 0,90 mm) for structural use in concrete, mortar or grout</i></p>							
<p>Tensile properties / Modulus of elasticity:</p> <table><tr><td>- tensile strength:</td><td>280 N/mm²</td></tr><tr><td>- elastic modulus:</td><td>NPD</td></tr></table> <p>Effect on consistence of concrete:</p> <table><tr><td>- increase of Vebè time with 1 kg/m³ fibres:</td><td>1,2 s</td></tr></table> <p>Effect on strength of concrete: NPD</p> <p>Release of dangerous substances: NPD</p>		- tensile strength:	280 N/mm ²	- elastic modulus:	NPD	- increase of Vebè time with 1 kg/m ³ fibres:	1,2 s
- tensile strength:	280 N/mm ²						
- elastic modulus:	NPD						
- increase of Vebè time with 1 kg/m ³ fibres:	1,2 s						

Note:

MAPEI supplies the current annex along with the DoP to make the consultancy of the CE marking easier for the international clients. The enclosed CE marking can be slightly different compared to the one printed on the relevant packaging or documentation because of:

- NPD values can be omitted by the CE marking
- graphic adaptations due to lack of space on the packaging or printing methods used,
- different language (the same packaging can be shared by several countries),
- the product is already in stock when the updating of the CE marking is implemented,
- printing mistakes.