

# ***Mapecoat Wet & Dry R11***

## ***Mapecoat 4 LVT***



# **Mapecoat Wet & Dry R11**

## **Mapecoat 4 LVT**



### **Mapecoat Wet & Dry R11** **per pavimenti resilienti di ogni tipo**

### **Mapecoat 4 LVT** **per pavimenti e rivestimenti in LVT**

Finiture protettive trasparenti, disponibili in versione opaca (10 gloss) e semilucida (30 gloss). Conferiscono caratteristiche antiscivolo ed elevata resistenza all'usura ed all'abrasione ai pavimenti resilienti e in LVT, ad uso civile e commerciale, anche sottoposti a elevato traffico pedonale.

### **Mapecoat Wet & Dry R11** **for all types of resilient flooring**

### **Mapecoat 4 LVT** **for LVT floor and wall coverings**

*Transparent protective finishes, available in matt (10 gloss) and semi-gloss (30 gloss). These products form a non-slip finish with high resistance to wear and abrasion on resilient and LVT flooring in civil and commercial surroundings, including areas subjected to high volumes of foot traffic.*



**DIN 51130**  
**AS 4586**



**DIN 51097**  
**AS 4586**





## **Mapecoat 4 LVT**

### **PROPRIETÀ DEI PRODOTTI**

- Resistenza allo scivolamento secondo DIN51130 e AS 4586: R11
- Resistenza allo scivolamento a piedi nudi secondo DIN 51097 e AS4586: A+B
- Resistenza allo scivolamento secondo EN 13036-4 (metodo del pendolo): 90 (superficie asciutta); 55 (superficie bagnata - classe P5 secondo AS4586)
- Elevata resistenza all'abrasione e alla rigatura.
- Alta resistenza ai raggi ultravioletti, non ingiallenti.
- Proteggono le pavimentazioni dai raggi ultravioletti.
- Sigillano i giunti degli LVT e delle pavimentazioni resilienti in piastre soggette a frequenti lavaggi e dilavamenti.
- Resistono a diversi aggressivi chimici.
- Inodore.
- Facili da applicare.
- Prive di solventi.
- Certificate EMICODE EC1 R (a bassissime emissioni).
- Innocue per la salute dell'applicatore e dell'utilizzatore finale.

### **PRODUCT PROPERTIES**

- *Slip resistance according to DIN 51130 and AS 4586: R11.*
- *Barefoot slip resistance according to DIN 51097 and AS 4586: A+B.*
- *Slip resistance according to EN 13036-4 (pendulum test method): 90 (dry surface); 55 (wet surface - class P5 according to AS4586)*
- *High resistance to abrasion and scuff marks.*
- *High resistance to UV rays: do not yellow.*
- *Protect floors from UV rays.*
- *Seal joints in LVT and resilient tiled flooring subjected to frequent cleaning cycles and rinsing.*
- *Resistant to various aggressive chemicals.*
- *Odourless.*
- *Simple application.*
- *Solvent-free.*
- *Certified EMICODE EC1 R (very low emission).*
- *Harmless for floor installers and end users.*



## Mapecoat Wet & Dry R11

### Dati Tecnici / Technical Data

#### Dati identificativi del prodotto / Product details

	Parte A / Component A	Parte B / Component B
Consistenza / Consistence:	<b>liquido</b> <i>liquid</i>	<b>liquido</b> <i>liquid</i>
Colore / Colour:	<b>bianco lattiginoso</b> <i>milky white</i>	<b>trasparente incolore</b> <i>transparent, colourless</i>
Densità (g/cm <sup>3</sup> ) / Density (g/cm <sup>3</sup> ):	<b>1.025</b>	<b>1.075</b>

#### Dati applicativi (a +23°C e 50% U.R.) / Application data (at +23°C and 50% R.H.)

Rapporto di miscelazione / Mixing ratio:	<b>5 : 1</b>
Fuori polvere / Dust dry:	<b>30 mins</b>
Fuori impronta / Touch dry:	<b>50 mins</b>
Sovraverniciabilità / Paintability (if required):	<b>min. 2 h - max. 48 h (dopo oltre 48 h è necessario preparare adeguatamente la superficie con Ultracoat Pad rosso o verde)</b> <i>min. 2 hours - max. 48 hours (after more than 48 hours the surface will need to be prepared with a red or green Ultracoat Pad)</i>
Pedonabilità / Set to foot traffic:	<b>16 h</b> <b>16 hours</b>
Messa in esercizio / Ready for service:	<b>24 h</b> <b>24 hours</b>

#### Prestazioni finali / Final performance

Grado di brillantezza (valore indicativo) / Gloss (Indicative value):	<b>10-30</b>
Resistenza allo scivolamento secondo DIN 51130 e AS 4586 / Slip resistance according to DIN 51130 and AS 4586:	<b>R11</b>
Resistenza allo scivolamento a piedi nudi secondo DIN 51097 e AS 4586 / Barefoot slip resistance according to DIN 51097 and AS 4586:	<b>A+B</b> <b>A+B</b>
Resistenza allo scivolamento secondo EN 13036-4 e AS 4586 (metodo del pendolo) / Slip resistance according to EN 13036-4 and AS 4586 (pendulum test method):	<b>Asciutto: 90</b> <b>Bagnato: 55 (classe P5 secondo AS 4586)</b> <b>Dry: 90</b> <b>Wet: 55 (class P5 according to AS 4586)</b>

**SEDE**  
**MAPEI SpA**  
Via Cafiero, 22 - 20158 Milano  
Tel. +39-02-37673.1  
Fax +39-02-37673.214  
Internet: [www.mapei.com](http://www.mapei.com)  
E-mail: [mapei@mapei.it](mailto:mapei@mapei.it)

